

▲ NITRON ONE®

BLUE
NITRILE
NON-STERILE
AMBIDEXTROUS
FULLY TEXTURED
BEADED CUFF
FOR SINGLE USE ONLY

NON-LATEX

LIGHTLY POWDERED EXAMINATION GLOVES

For those who prefer a lightly powdered nitrile glove, but require strength for difficult jobs, Microflex offers the Nitron One® glove. The fully textured surface provides a sure grip whether working in wet or dry environments.

- Lightly powdered with absorbable cornstarch (USP)
- Thickest at the palm and finger for increased protection
- Fully textured for an enhanced grip





| PRODUCT CODE | | | |
|--------------|-----------|--|--|
| S | NO-123-S | | |
| М | NO-123-M | | |
| L | NO-123-L | | |
| XL | NO-123-XL | | |

| PACKAGING | | |
|-----------|------------|--|
| 100 | Gloves/Box | |
| 10 | Boxes/Case | |
| | | |

| GLOVE PROFILE | | ASTM D 6319 | NITRON ONE® |
|-----------------------|-----------------------------|----------------------|-------------|
| Length | mm (inches) | min. 220 (8.7) | 245 (9.6) |
| Cuff Thickness | mm (mils) | n/a | 0.11 (4.3) |
| Palm Thickness | mm (mils) | min. 0.05 (2.0) | 0.14 (5.5) |
| Finger Thickness | mm (mils) | min. 0.05 (2.0) | 0.18 (7.1) |
| Tensile Strength | Before Aging After Aging | min. 14 min. 14 | 18 24 |
| Elasticity/Elongation | Before Aging After Aging | min. 500 min. 400 | 500 400 |
| Pinhole Defect Rate* | (AQL) | max. 2.5 | 2.5 |

^{*} Pinhole Defect Rate is FDA minimum requirement.









RECOMMENDED INDUSTRIES

